

GISSFIX PT 88

Dispersing agent/deflocculant



Chemical basis:

Preparation of phosphonates

Characteristics:

Appearance: white granules
Active matter: approx. 75 %
Bulk density (20 °C): approx. 1000 g/l
pH (1 %): approx. 6
Iron content: max. 35 ppm

Shelf-life / Packaging:

6 months under proper storage conditions
bags of 25 kg

Application:

GISSFIX PT 88 is suitable for the deflocculation of bodies of differing composition. It makes it possible to prepare slips with a high solids content and low viscosity.

The deflocculating effect of GISSFIX PT 88 is a result, on the one hand, of cation exchange of the additive with the ceramic body, and the influence on the electrical double layer of the clay mineral particles that is associated with this. On the other hand, it has complexing effect on metal ions and thus can bind Mg- or Ca-ions which disturb the deflocculation.

The deflocculating effect of GISSFIX PT 88 can be optimised by combination with other deflocculants, such as for example GISSFIX ZS.

Since, on account of their differing mineralogical composition, raw materials react very differently to various deflocculants and the amounts added, we recommend comparative trials.

The above results have been obtained from trials in our laboratory and plant. In the light of changing conditions they can serve only as a guide and are therefore offered without obligation. We ask you to observe the possible rights of third parties.