



DECOFLUX GL 26

Printing medium for glass



Chemical basis:

Preparation of polymers in solvents

Characteristics:

Appearance: colourless to yellowish liquid
Solubility: water-miscible
Density: approx. 0.97 g/cm³
Viscosity (20°C): approx. 120 mPas

Shelf-life / Packaging:

12 months under proper conditions
drums of 25 and 130 kg, containers of 1000 kg

Application:

DECOFLUX GL 26 is a solvent based water-miscible printing medium for glass that can be cleaned with water.

It is suitable for screen printing and roller coating.

For screen printing it has a high pasting ratio and very good leveling properties.

The approximate pasting ratio depending on the particle size of the glass colour powder will be:

	1 part	DECOFLUX GL 26
	5 parts	glass colour powder (lead containing)
or	4 parts	glass colour powder (lead free).

DECOFLUX GL 26 is designed for use with IR drying systems and has a clean burn out in a standard glass firing cycle.

The above results have been obtained from trials in our laboratory and plant. In the light of changing conditions they can serve only as a guide and are therefore offered without obligation. We ask you to observe the possible rights of third parties.