



DOLAPIX FF 44

Dispersant and deflocculant



Chemical basis:

Phosphate preparation

Characteristics:

Appearance: grey powder
Solubility: partly water-soluble
Bulk density: approx. 300 g/l
pH (10 %): approx. 6.5
Na₂O: approx. 7 %
Residue on ignition: approx. 80 %

Shelf-life / Packaging:

6 months under proper and dry conditions
bags of 20 kg

Application:

DOLAPIX FF 44 is a phosphate preparation, which is used for the deflocculation of refractory bodies.

DOLAPIX FF 44 shows a broad deflocculation interval and is also effective in cement-bonded bodies.

It is particularly suitable for dispersing microsilica containing, alumina bonded self-flowing castables.

The required addition quantity ranges between 0.1 and 1.0% of the whole mix.

The above results have been obtained from trials in our laboratory and plant. In the light of changing conditions they can serve only as a guide and are therefore offered without obligation. We ask you to observe the possible rights of third parties.